



PARSON ADHESIVES, INC.

675 Tennyson Drive Rochester, MI 48307

Phone (248) 299-5585 Fax (248) 299-3846 Email: sales@parsonadhesives.com

SONLOK 3290 Anaerobic Thread Locking Compound

SONLOK 3290 is a fast curing, medium strength anaerobic thread-locking compound for bonding and sealing threads, and retaining of cylindrical parts.

SONLOK 3290 is highly resistance to heat, vibrations, water, gases, oils, hydrocarbons and many chemicals.

◆ **Application**

- Penetrates threads by capillary action. Medium strength threadlocker.
- Ideal for sealing hairline cracks, small nuts and bolts.
- Seals and welds porous metal parts. Localize heating and hand tools are needed for disassembly. Prevents corrosion and leakage.
- Secure setscrews and other assemblies after settings are completed.
- Fasteners on vibrating machines or moving components.
- Meets Military specifications: MIL-S-46163A Type III Grade R and MIL-S-22473E Letter Grade AA

◆ **Physical Properties**

Description	Specification
Composition	Methacrylate Ester
Color	Green
Viscosity @ 25 °C,	10-20 cps
Specific Gravity	1.05
Maximum Diameter of Thread/Gap Filling	M 5/ 1/2 " / 0.07 mm
Flash Point	> 100 °C
Solvent Content	None
Shelf Life	1 year

◆ **Curing Properties**

Description	Specification
Handling Cure Time	10-20 minutes
Functional Cure Time	1-3 hours
Full Cure Time	24 hours
Shear Strength	8 - 12 N/mm ²
Locking Torque	
- Breakaway	15 - 25 N.m
- Prevailing	30 - 40 N.m
Temperature Range	-55 to 150 °C

◆ **Chemical Resistance**

Chemical	Temp.	% Initial Strength Retained	
		500 hours	1000 hours
Acetone	22 °C	90	85
Ethanol	22 °C	85	85

Motor Oil	125 °C	85	65
Gasoline	22 °C	65	55
Brake Fluid	22 °C	90	85
Water/Glycol	87 °C	90	90

◆ Application Method

Surfaces should be dry, clean, and free of any contamination. Thread locker should be applied to the bolt in sufficient quantity to fill threads. SONLOK 3290 performs the best in thin bond gaps. This thread locker is specifically formulated to give controlled friction and torque/tension ratio during assembly.

◆ Storage

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 46 °F to 82 °F. Please do not return any unused material to its original container.

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the.

Warranty: All products purchased from or supplied by Parson are subject to terms and conditions set out in the contract. Parson warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Parson is considered accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Parson makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

Parson Adhesives, Inc. 675 Tennyson Drive, Rochester, MI 48307

Toll Free-Phone: 1-877-805-0185 Fax: (248) 299-3846 E-mail: sales@parsonadhesives.com