



## PARSON ADHESIVES, INC.

675 Tennyson Drive Rochester, MI 48307

Phone (248) 299-5585 Fax (248) 299-3846 Email: [sales@parsonadhesives.com](mailto:sales@parsonadhesives.com)

---

### **SONLOK™ 3660** **Retaining Compound**

SONLOK 3660 is a fast curing; paste like consistency, high strength anaerobic retaining compound for cylindrical fitting parts particularly where bond gaps can approach 0.50mm. This product offers very good gap cure properties.

SONLOK 3660 retaining compound is a single component anaerobic adhesive, which develops high strength rapidly when confined in the absence of air between close fitting metal surfaces.

#### **Applications:**

- Ideal to fill gaps up to 0.50 mm diameter clearance.
- Used for restoring correct fits on worn shafts, spun bearings and damaged keyways.
- Excellent retaining, sealing and thread locking compound.

#### **Physical Properties:**

Composition:	Urethane Methacrylate
Color:	Grey
Viscosity:	1, 225,000 cps at 25 °C
Brookfield HBT	
Specific Gravity:	1.15
Maximum Diameter of Thread/Gap Filling:	0.50 mm
Flash Point:	> 93 °C
Solvent Content:	None
Shelf Life:	1 year

#### **Curing Properties:**

Handling Cure Time:	10 - 30 minutes
Functional Cure Time:	3-4 hours
Full Cure Time:	24 hours
Shear Strength:	16 - 26 N/mm <sup>2</sup>
DIN 54452	
Coefficient of thermal expansion ASTM D696 K <sup>-1</sup>	80 x 10 <sup>-6</sup>
% Elongation at Break	<2

**PRECAUTIONS:** This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

**Warranty:** All products purchased from or supplied by Parson are subject to terms and conditions set out in the contract. Parson warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Parson is considered accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Parson makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.